

## **Features**

- •TIME®5430 Shore A hardness tester for testing the hardness of soft rubber, plastics and other elastomeric materials
- •TIME<sup>®</sup>5431 Shore D hardness tester for testing the hardness of hard plastics and rubbers.
- •TIME®5432 Shore AO hardness tester is mainly used to test soft materials like low hardness rubber and sponge.
- •TIME®5432C hardness tester for testing microporous materials for shoes made of rubber and plastic.
- •TIME<sup>®</sup>5433 Shore AM hardness tester is designed to test thin samples such as vulcanized rubber and plastic products.
- It adopts LVDT displacement sensor, which is accurate and can work in harsh environment
- •The OLED screen clearly shows the hardness value. Menu operation.
- •Automatic Zero point calibration.
- •Three work modes to meet varied testing requirements: real-time, peak-value-lock and timing-lock.
- •In peak-value-lock mode, the instrument can automatically lock the peak hardness value.
- •In timing-lock mode, set the timing from 1 to 60 seconds. It automatically starts timing and locks the measured value.
- •In the lock modes, the upper and lower limits of the measured value can be preset, and a prompt is displayed when out of the limit,
- which is convenient for batch detection. It can also calculate the average value and automatically removing gross errors. •Store 200 average lock values.
- •Optional software is offered to transfer the test data to PC via USB in the format of Microsoft Word or Excel.

## **Technical Specification**

Model	TIME <sup>®</sup> 5430 (hardness<20HD)	TIME <sup>®</sup> 5431 (hardness >90HA)	TIME <sup>®</sup> 5432 (hardnesss<20HA)	TIME <sup>®</sup> 5432C	TIME <sup>®</sup> 5433 (thickness: <6mm)
Hardness scale	Shore A	Shore D	Shore AO	Asker-c	Shore AM
Data output	USB				
Measuring range	0~100HA	0~100HD	0~100HAO	0~100Hc	0~100HAM
Tolerance	≤±1HA(20~90)	≤±1HD(20~90)	≤±1HAO(20~90)	≤±1Hc(20~90)	≤±1HAM(20~90)
Display resolution	0.1HA	0.1HD	0.1HAO	0.1Hc	0.1HAM
Power supply	Built in rechargeable battery				
Operating temperature	0~40°C				
Continuous working time	24 hours				
Dimensions (mm)	173×56 ×42	173×56 ×42	173×56 ×42	168×56 ×42	173×56 ×42
Weight (g)	200	200	200	249	200